

Soudal Joint Finish

Revision: 20/04/2021

Page 1 from 1

Technical data

Basis	Water with specific detergents
Consistency	Fluid
Density	1,00 g/ml
Application temperature	5 °C → 35 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Soudal Joint Finish is used for perfect smoothening of all types of joints.

in case of a paintable sealant.

Properties

- Easy application
- pH neutral
- Minimal skin irritation
- Biodegradable
- Ready to use and very user friendly

Applications

- Smoothening of joints created with most common types of sealants (silicones, polyurethane and MS polymers).

Packaging

Colour: colourless

Packaging: 500 ml

Shelf life

2 years in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Application method

Application method: Spray the product on the joint sealant. Moisten a finger or spatula with the product. Smooth the joint with finger or spatula.

Finishing: After sufficient skinning of the sealant rinse Finishing Liquid away with clean water. Avoid drying in of Finishing Liquid on the sealant surface or adjacent materials. Dried residue of Finishing Liquid may cause optical degradation of the upper layer of the silicone and adjacent materials. Residues may also adversely affect the adhesion of the paint

Health- and Safety Recommendations

Take the usual labour hygiene into account.

Remarks

- The product contains no solvents and hence doesn't damage the most common substrates.
- We strongly recommend not to apply the product in full sunlight as it will dry very fast.
- On certain surfaces can cause staining.
- A preliminary test is always recommended.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.