



## Polystyrene Adhesive 28A

Revision: 13/12/2016

Page 1 from 2

### Technical data

Basis	(Styrene) Acrylate
Consistency	Paste
Curing system	Physical drying
Density	Ca. 1,83 g/ml
Temperature resistance	-20°C till +70°C (cured)
Open time	10 - 15 min.
Consumption (*)	1000-1500 g/m <sup>2</sup> at full surface bonding, depending on substrate and used trowel. Minimum 200 g/m <sup>2</sup> when using dots for bonding.
Application temperature	5 °C → 30 °C
Drying time (20°C and 60% R.H.)	Ca. 24 h
Total solid content	Ca. 82 %

(\*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

### Product description

Polystyrene Adhesive 28A is a ready to use adhesive paste for the interior bonding of polystyrene products onto porous substrates.

### Properties

- paste ready for use
- High adhesive strength
- Solvent free
- Not flammable

### Applications

- Bonding of soft and hard polystyrene.
- Bonding of synthetic foam materials.
- Bonding of polystyrene ceiling tiles.
- Bonding of foamed insulation materials on walls and floors.

### Packaging

Colour: white

Packaging: 1 kg plastic pot, 5 kg bucket, 15 kg bucket

### Shelf life

At least 24 months in unopened packaging in a dry storage place at temperatures between +5°C and +25°C.

### Substrates

Substrates: Porous surfaces such as stone, concrete, plaster, wood.

Nature: flat, clean, dry, free of dust and grease.

Surface preparation: On very absorbent surfaces the surface should be treated with a primer.

We recommend a preliminary adhesion test on any substrate.

### Application method

Application method: Apply the adhesive on the substrate using a notched trowel or dots. Don't apply more adhesive on the substrate as you can handle within 10 minutes. When bonding polystyrene panels or ceiling tiles, apply them with a sliding movement into the adhesive and press firmly.


Cleaning: Before curing, Polystyrene Adhesive 28A can be removed with water from substrates and tools. Cured Polystyrene Adhesive 28A can only be removed mechanically.

Repair: With the same material

### Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.



---

## Polystyrene Adhesive 28A

---

Revision: 13/12/2016

Page 2 from 2

**Environmental clauses**

Leed regulation:

Polystyrene Adhesive 28A conforms to the requirements of LEED. Low –Emitting

Materials: Adhesives and Sealants. SCAQMD rule 1168. VOS-level &lt; 50 g/L

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.